EPOXY TINT PACK

Tint Pack for 100% Solids Epoxy

Product Description

Epoxy Tint Pack is a 100% solids, concentrated, tint system specially formulated for 100% solids Electric Epoxy or 100 Epoxy. Epoxy Tint Pack is formulated with high quality, ultra fine particle pigments that easily disperses in Electric Epoxy or 100 Epoxy. Epoxy Tint Pack is a superior choice to obtain a semi transparent stain or a solid opaque colored finish in Electric Epoxy or 100 Epoxy

Benefits & Features

- 14 brilliant standard colors to choose from. *Includes black & white
- Very economical, easy and decorative way to coat a variety of concrete substrates
- Easily disperses into Electric Epoxy or 100 Epoxy
- Very easy way to create a beautiful, solid color concrete surface
- Try in epoxy for the base coat of Liquid Metals

50°F - 80°F

Recommended Applications

Epoxy Tint Pack is effective on applications such as auto service centers, warehouses, laboratories, aircraft hangars, cafeterias, garages, quartz & metallic flooring base coats and many other concrete surfaces where a solid color, high build is desired.

Technical Information

Application Temp

Solids Concentrated Wet Appearance Depends on Color Chosen
Dry Time - Tack Free See Epoxy Data Sheet Dry Appearance Tinted and High Gloss
Dry Time - Foot Traffic See Epoxy Data Sheet VOC Content N/A
Dry Time - Heavy Traffic See Epoxy Data Sheet
Re-Coat Time Window See Epoxy Data Sheet

Specifications/Compliances

Approximate Usage Rates

1 Epoxy Tint Pack per 3 Gallons of Epoxy

*Usage rates are suggested amounts only! Due to varying substrates, surface texture, porosity and desired look a test area is recommended to achieve desired results.

Shelf Life

Up to one year from manufacture date in its original, unopened container stored at room temperature.

Packaging

Available in 1 pint containers

ORRVILLE 133 North Kohler Road Orrville, Ohio 44667 (330) 682-5678 CLEVELAND
7941 Granger Road
Cleveland, Ohio 44125
(216) 573-0770

COLUMBUS 690 Harrison Drive Columbus, Ohio 43204 (614) 253-3326





^{***}Testing in accordance with procedures outlined in EPA Method 24, "Volatile Organic Content VOC of Paints and Related Coatings". The solids content was determined in accordance with ASTM D 5095 and the VOC was calculated in accordance with ASTM D 3960.

Instructions for Use

<u>Surface Preparation:</u> Concrete surface must be clean and free of all contaminants and water. Do not apply if rain is forecast within 24 hours. If moisture is present or if the surface is not clean and free of all contaminants, the sealer may have white spots and have premature delamination and failure.

Review the technical data and SDS for the Electric Epoxy or 100 Epoxy prior to use for surface prep instructions, application instructions, coverage rates and limitations.

Substrate and air temperature must be no less than 40°F and not exceed 80°F. If applied outside these limits the sealer may not achieve adequate film formation and may have excessive air entrapment, bubbles, blushing and hazing. Note that in direct sunlight, substrate temperature can exceed 150°F which can cause extreme bubbling issues.

<u>Mixing:</u> Mix desired amount in Epoxy Part A for 1-2 minutes using a squirrel mixer at a slow speed to avoid introducing air to the products prior to mixing parts A & B. Material may separate during long term storage. Remix as needed.

<u>Application</u>: Review the technical data and SDS for the Electric Epoxy or 100 Epoxy prior to use for surface prep instructions, application instructions, coverage rates and limitations.

FOR PERSONAL PROTECTION USE GLOVES, GOGGLES, AND RESPIRATORS.

CAUTION: Do not add too much color! Apply a test area prior to job application for desired appearance. Over pigmenting may cause color float or streaking, especially in the darker colors! Do not allow to puddle! The average usage is 1 Epoxy Tint Pack pint per 3 gallons of material for most opaque applications. For lighter colors it may take more and darker colors may take less depending on the application as well as the composition of the epoxy.

Check Epoxy Tint Pack for compatibility with the competitors' 100% solids epoxy prior to use!

Please Note: It is always recommended to test the product in a small, inconspicuous area (on the same concrete substrate) for desired results prior to application. Coverage rates may vary for all coatings and substrates depending on porosity, density, texture etc.

Clean-Up

Use xylene. Dispose of containers in accordance with local, state and federal regulations.

Product Removal

Refer to epoxy technical data sheet

Precautions & Limitations

- This product will not freeze during storage, however, allow temperature to rise to 50°F prior to application.
- All HVAC ventilation ducts should be somehow blocked prior to application so solvent fumes are not distributed
- If using indoor, use proper ventilation while applying and for hours after application to ensure fumes are removed.
- It is not recommended to apply product over carpet, tile, or other types of floor adhesives
- This product performs best when applied as one or two medium-light coats, not one heavy coat.
- Please be aware that this product when cured may be slippery when wet. An anti-slip additive, such as Deco Grip, can be added to reduce slip hazards.
- This product is not resistant to brake fluid, gasoline, and may similar products.
- It is not recommended to thin product. Improper thinning may cause sealer to delaminate in a short time frame.
- This product may darken the surface of many new and existing concrete slabs. Test prior to use.
- Follow the instructions for the Electric Epoxy or 100 Epoxy that is to be used for application guidelines.

Special Notes

Please consult Safety Data Sheet (SDS) and read warranty information prior to use. This information can be requested by contacting customer service at 330-682-5678.

ORRVILLE 133 North Kohler Road Orrville, Ohio 44667 (330) 682-5678 CLEVELAND
7941 Granger Road
Cleveland, Ohio 44125
(216) 573-0770

COLUMBUS 690 Harrison Drive Columbus, Ohio 43204 (614) 253-3326



